

AD-A161 733

ELASTIC-PLASTIC LOADING AND UNLOADING IN A THICK TUBE
WITH KINEMATIC HARD. (U) ARMY ARMAMENT RESEARCH AND
DEVELOPMENT CENTER WATERVLIET NY L... P C CHEN SEP 85

1/1


UNCLASSIFIED

ARLDB-TR-85032 SBI-AD-E440 302

F/O 20/11

NL

											END		
											FILED		
											DTF		



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

AD-A161 733

AD

TECHNICAL REPORT ARLCB-TR-85032

**ELASTIC-PLASTIC LOADING
AND UNLOADING IN A THICK TUBE
WITH KINEMATIC HARDENING THEORY**

PETER C. T. CHEN

SEPTEMBER 1985

SELECTED
OCT 22 1985
JPA



**US ARMY ARMAMENT RESEARCH AND DEVELOPMENT CENTER
LARGE CALIBER WEAPON SYSTEMS LABORATORY
BENET WEAPONS LABORATORY
WATERVLIET N.Y. 12189**

DTIC FILE COPY

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

88 10 22 010

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacture(s) does not constitute an official indorsement or approval.

DISPOSITION

Destroy this report when it is no longer needed. Do not return it to the originator.

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	1
ELASTIC-PLASTIC LOADING	1
REVERSE YIELDING	3
ELASTIC-PLASTIC UNLOADING	4
NUMERICAL RESULTS AND DISCUSSIONS	6
REFERENCES	9

LIST OF ILLUSTRATIONS

1. Effect of hardening on the relation between internal pressure and elastic-plastic interface.	11
2. Boundary displacement during loading and after unloading.	12
3. Distribution of hoop stresses during loading.	13
4. Distribution of residual hoop stresses.	14
5. Effect of hardening parameter on residual stress distribution.	15
6. Effect of hardening rules on residual stress distribution.	16



Availability Codes	
Dist	Avail and/or Special
A1	

INTRODUCTION

The importance of the determination of residual stresses in a prestressed thick-walled cylinder is well-known, and elastic-plastic loading response has been extensively studied (refs 1-5). Most of the earlier solutions for residual stresses were based on the assumption of elastic unloading and only a few considered elastic-plastic unloading (refs 2,5). Bland's work (ref 2), which neglects the Bauschinger effect, is based on the Tresca's yield criterion and the isotropic hardening rule. Kinematic hardening is the simplest theory that can model the Bauschinger effect (refs 6,7). If unloading does not occur, there is no difference between the kinematic and isotropic hardening models. For unloading with reverse yielding, the results based on these two models will be different as shown in a recent paper (ref 5) using the ADINA finite element code (ref 8). The von Mises' yield criterion and its associated flow rules were used in both models.

This report states a closed-form solution for elastic-plastic loading and unloading in pressurized thick-walled cylinders using Tresca's yield criterion, its associated flow rule, and the linear kinematic hardening law. Numerical results are presented for a closed-end tube.

ELASTIC-PLASTIC LOADING

Consider a thick-walled cylinder, internal radius a and external radius b , which is subjected to internal pressure p . The material is assumed to be elastic-plastic, obeying the Tresca's yield criterion, the associated flow theory, and a linear strain-hardening rule. Using the isotropic hardening

References are listed at the end of this report.

theory, the elastic-plastic solution has been obtained by Bland (ref 2). In order to consider the Bauschinger effect, the kinematic hardening theory is used here. Subject to the condition $\sigma_\theta > \sigma_z > \sigma_r$, Tresca's yield criterion for the Prager-hardening rule (ref 6) states that yielding occurs when

$$(\sigma_\theta - \alpha_\theta) - (\sigma_r - \alpha_r) = K_0 \quad (1)$$

where

$$\alpha_\theta = c \epsilon_\theta^p, \quad \alpha_r = c \epsilon_r^p \quad (2)$$

define the position of the center of the yield surface; c is a material constant and K_0 the initial yield stress. The associated flow rule states that

$$d\epsilon_\theta^p = -d\epsilon_r^p \quad \text{and} \quad d\epsilon_z^p = 0 \quad (3)$$

For the case of linear strain-hardening, the yield stress curve can be represented by a straight line,

$$K/K_0 = 1 + \eta \epsilon^p \quad \text{and} \quad \eta = (E/K_0)^m / (1-m) \quad (4)$$

where η is a material constant and the equivalent plastic strain ϵ^p is defined by

$$\epsilon^p = \sqrt{2/3} \int \{ (d\epsilon_\theta^p)^2 + (d\epsilon_r^p)^2 \}^{1/2} = \frac{2}{\sqrt{3}} \epsilon_\theta^p \quad (5)$$

The elastic-plastic solution for the stresses and displacements can be obtained explicitly. The expressions in the plastic range ($a < r < \rho$) are

$$\sigma_r/K_0 = \frac{1}{2} \left(1 + \frac{\rho^2}{b^2} \right) + \frac{1}{2} \eta \beta \left(\frac{\rho^2}{r^2} - 1 \right) - (1 - \eta \beta) \log \frac{\rho}{r} \quad (6)$$

$$\sigma_\theta/K_0 = \frac{1}{2} \left(1 + \frac{\rho^2}{b^2} \right) + \frac{1}{2} \eta \beta \left(\frac{\rho^2}{r^2} - 1 \right) - (1 - \eta \beta) \log \frac{\rho}{r} \quad (7)$$

$$\sigma_z/K_0 = \nu \rho^2/b^2 - 2\nu(1-\eta\beta) \log \frac{\rho}{r} + E\epsilon_z/K_0 \quad (8)$$

$$(E/K_0)(u/r) = (1-2\nu)(1+\nu)(\sigma_r/K_0) - \nu E\epsilon_z/K_0 + (1-\nu^2)\rho^2/r^2 \quad (9)$$

and in the elastic range ($\rho < r < b$)

$$\sigma_r/K_0 = \frac{1}{2} \left(\frac{\rho^2}{b^2} \mp \frac{\rho^2}{r^2} \right) \quad (10)$$

$$\sigma_\theta/K_0 = \frac{1}{2} \left(\frac{\rho^2}{b^2} \mp \frac{\rho^2}{r^2} \right) \quad (11)$$

$$\sigma_z/K_0 = E\epsilon_z/K_0 + \nu\rho^2/b^2 \quad (12)$$

$$(E/K_0)u/r = \frac{1}{2} (1+\nu) [\rho^2/r^2 + (1-2\nu)\rho^2/b^2] - \nu E\epsilon_z/K_0 \quad (13)$$

where

$$E\epsilon_z/K_0 = \frac{(\mu-2\nu)}{(b^2/a^2-1)} (p/K_0) \quad (14)$$

$$\mu = 0 \text{ (open-end) } , \quad 1 \text{ (closed-end)}$$

and

$$\beta^{-1} = \eta + \frac{\sqrt{3}}{2} (E/K_0)/(1-\nu^2) \quad (15)$$

The yield surface moves in translation during plastic deformation as given by

$$\alpha_\theta = -\alpha_r = (\sqrt{3}/2)c\epsilon^p \quad \text{and} \quad \epsilon^p = \beta(\rho^2/r^2-1) \quad (16)$$

The elastic plastic surface ρ is related to the internal pressure p by

$$p/K_0 = \frac{1}{2} (1-\rho^2/b^2) + (1-\eta\beta)\log \rho/a + \frac{1}{2} \eta\beta (\rho^2/a^2-1) \quad (17)$$

REVERSE YIELDING

If the pressure p given by Eq. (17) is subsequently removed completely with no reverse yielding, the unloading is entirely elastic and the solution is given by

$$\sigma_r' = \frac{p}{b^2/a^2-1} \left[\pm \frac{b^2}{r^2} - 1 \right] \quad (18)$$

$$\sigma_\theta' = \frac{p}{b^2/a^2-1} \left[\pm \frac{b^2}{r^2} - 1 \right] \quad (19)$$

$$\sigma_z' = \nu(\sigma_r' + \sigma_\theta') + E\epsilon_z' \quad (20)$$

$$E\epsilon_z' = -(\mu-2\nu)p/(b^2/a^2-1) \quad (21)$$

$$Eu'/r = -[(1-\nu - \mu\nu) + (1+\nu)b^2/r^2]p/(b^2/a^2-1) \quad (22)$$

The residual stress system, which will be denoted by two primes, is the sum of the system produced by loading and that produced by unloading, i.e., $\sigma_r'' = \sigma_r + \sigma_r'$, etc. Assuming the kinematic hardening rule and using Tresca's criterion subject to $\sigma_r'' > \sigma_z'' > \sigma_\theta''$, the reverse yielding will not occur if

$$(\sigma_r'' - \alpha_r) - (\sigma_\theta'' - \alpha_\theta) \leq K_0 \quad (23)$$

Substituting the loading and unloading solution into Eq. (23), we can determine the minimum pressure (p_m) for reverse yielding to occur. The equation for p_m is given by

$$p_m/K_0 = (1 - a^2/b^2) \quad (24)$$

Equating Eqs. (17) to (24), we can determine the maximum amount of overstrain for reverse yielding not to occur.

ELASTIC-PLASTIC UNLOADING

Now suppose that the loading has been such that the internal pressure is larger than p_m given by Eq. (24). On unloading, yielding will occur for $a \leq r \leq \rho'$ with $\rho' < \rho$. Using the kinematic hardening rule during unloading and assuming $\sigma_r'' > \sigma_z'' > \sigma_\theta''$, we have

$$(\sigma_r'' - \alpha_r'') - (\sigma_\theta'' - \alpha_\theta'') = K_0 \quad (25)$$

where

$$\alpha_r'' = c\epsilon_r''^p, \quad \alpha_\theta'' = c\epsilon_\theta''^p \quad (26)$$

Since the residual stress system is the sum of two systems produced by loading and unloading, combining Eqs. (1) and (25) leads to

$$(\sigma_r' - \alpha_r') - (\sigma_\theta' - \alpha_\theta') = 2K_0 \quad (27)$$

where

$$\alpha_r' = c\epsilon_r'^p, \quad \alpha_\theta' = c\epsilon_\theta'^p \quad (28)$$

During elastic-plastic unloading, the associated flow theory states that

$$d\epsilon_{\theta}'^P = -d\epsilon_r'^P < 0 \quad \text{and} \quad d\epsilon_z'^P = 0 \quad (29)$$

It has been assumed that the sign of $d\epsilon_{\theta}'^P$ is the same throughout the unloading process and that is negative. This will be the case when the internal pressure is removed during unloading. Since $\epsilon_z' = \epsilon_z'^e = -\epsilon_z$ is known, we can use Hooke's law and the equilibrium equation,

$$d\sigma_r'/dr = (\sigma_{\theta}' - \sigma_r')/r \quad (30)$$

to express σ_z' in terms of σ_r'

$$\sigma_z' = E\epsilon_z' + 2\nu\sigma_r' + \nu r(d\sigma_r'/dr) \quad (31)$$

Since the dilation is purely elastic

$$(du'/dr) + u'/r + \epsilon_z' = E^{-1}(1-2\nu)(\sigma_r' + \sigma_{\theta}' + \sigma_z') \quad (32)$$

On integration using Eqs. (30) and (31), we obtain

$$ru' = (1-2\nu)(1+\nu)E^{-1}r^2 \sigma_r' - \nu\epsilon_z'r^2 + A \quad (33)$$

where A is a constant. The strain components can be expressed in terms of σ_r' and $(d\sigma_r'/dr)$. The plastic strain components are

$$\epsilon_{\theta}'^P = -\epsilon_r'^P = Ar^{-2} - (1-\nu^2)E^{-1}r(d\sigma_r'/dr) \quad (34)$$

Using Eq. (31) together with Eqs. (27) and (28), we have

$$r(d\sigma_r'/dr) = -2(K_0 - c\epsilon_{\theta}'^P) \quad (35)$$

Substituting Eq. (35) into Eq. (34) and determining the constant A by the condition $\epsilon_{\theta}'^P = 0$ at ρ' , we obtain

$$A = -2(1-\nu^2)(K_0/E)\rho'^2 \quad (36)$$

and

$$(E/K_0)\epsilon_{\theta}'^P = -2(\rho'^2/r^2 - 1)/[2c/E + (1-\nu^2)^{-1}] \quad (37)$$

Equations (35) and (36) with the boundary condition at $r = a$ suffice to determine σ_r' in the plastic region. The expressions for the stresses in ($a <$

$r < \rho'$) are given explicitly by

$$\sigma_r'/K_0 = p/K_0 - \eta\beta(\rho'^2/a^2 - \rho'^2/r^2) - 2(1-\eta\beta)\log(r/a) \quad (38)$$

$$\sigma_\theta'/K_0 = \sigma_r'/K_0 - 2 - 2\eta\beta(\rho'^2/r^2 - 1) \quad (39)$$

$$\sigma_z'/K_0 = \nu(\sigma_r' + \sigma_\theta')/K_0 - E\epsilon_z/K_0 \quad (40)$$

and in $(\rho' < r < b)$ given by

$$\sigma_r'/K_0 = \pm (\rho'^2/r^2 \mp \rho'^2/b^2) \quad (41)$$

$$\sigma_\theta'/K_0 \quad (42)$$

$$\sigma_z'/K_0 = -2\nu\rho'^2/b^2 - E\epsilon_z/K_0 \quad (43)$$

The continuity condition of σ_r' determines the relation between ρ' and ρ as given by

$$\begin{aligned} 1 - \rho'^2/b^2 + 2(1-\eta\beta) \log \frac{\rho'}{a} + \eta\beta(\rho'^2/a^2 - 1) \\ = \frac{1}{2} (1 - \rho^2/b^2) + (1-\eta\beta)\log(\rho/a) + \frac{1}{2} \eta\beta(\rho^2/a^2 - 1) \end{aligned} \quad (44)$$

The yield surface moves in translation during elastic-plastic unloading according to

$$\alpha_\theta' = -\alpha_r' = c\epsilon_\theta'^P \quad (45)$$

where $\epsilon_\theta'^P$ is given by Eq. (37).

NUMERICAL RESULTS AND DISCUSSIONS

Consider a closed-end thick-walled cylinder with the following parameters: $b/a = 3$, $\nu = 0.3$, and $E/K_0 = 200$. The numerical results for the displacements, strains, and stresses during elastic-plastic loading and unloading have been calculated. Figure 1 shows the relationship between the internal pressure factor (p/K_0) and the dimensionless elastic-plastic interface (ρ/a) for various values of the hardening parameter, $m = 0, 0.05$,

0.1, and 0.2. The displacements at the inside and outside boundaries of the tube (U_a and U_b) are shown in Figure 2 as functions of the elastic-plastic interface for $m = 0.1$. The solid and dotted curves represent the displacements during loading and after unloading, respectively. Figure 3 shows the distribution of hoop stresses (σ_θ) during loading for $\rho/a = 1.0, 1.5, 2.0, 2.5$, and 3.0 . After complete unloading from different stages of loading, the corresponding residual hoop stresses (σ_θ'') are shown in Figure 4. Reverse yielding occurs in a strain-hardening tube with $m = 0.1$ only when the plastic portion (ρ) is larger than $1.652 a$. In order to show the effect of hardening parameters (m) on the residual stress distribution, the numerical results are presented in Figure 5 for $m = 0, 0.05$, and 0.10 . As can be seen in the figure, larger values of hardening parameter (m) tend to reduce the beneficial residual hoop stress at the bore.

All the results presented in Figures 1 through 5 are based on the kinematic theory. We have also calculated the results based on the isotropic hardening theory (ref 2). Figure 6 shows a comparison of two hardening rules for the residual hoop stresses in a closed-end thick-walled cylinder. The dotted curves represent the isotropic hardening model with no Bauschinger effect. According to this model, there is no reverse yielding. The solid curves show the Bauschinger effect, and reverse yielding occurs in both cases, $\rho'/a = 1.098, 1.336$, for $\rho/a = 2.0, 3.0$, respectively. The residual hoop stresses at the bore are $\sigma_\theta''/K_0 = -0.729, -0.327$ for $\rho/a = 2.0, 3.0$, respectively. According to the isotropic hardening rule, those values of σ_θ''/K_0 should be $-1.060, -1.318$ for $\rho/a = 2.0, 3.0$, respectively. These numerical results indicate that the effect of hardening rules on the residual

hoop stresses is quite significant, especially near the bore. Many plasticity theories for reverse yielding have been proposed and reviewed (ref 9), and many computer programs have been developed (ref 10). It is believed that the numerical results based on other theories will fall within the limits obtained by using the kinematic and isotropic hardening models.

REFERENCES

1. Hill, R., Mathematical Theory of Plasticity, Oxford University Press, 1950.
2. Bland, D. R., "Elastoplastic Thick-Walled Tubes of Work-Hardening Materials Subject to Internal and External Pressures and Temperature Gradients," Journal of Mechanics and Physics of Solids, Vol. 4, 1956, pp. 209-229.
3. Chen, P. C. T., "The Finite Element Analysis of Elastic-Plastic Thick-Walled Tubes," Proceedings of Army Symposium on Solid Mechanics, The Role of Mechanics in Design-Ballistic Problems, 1972, pp. 243-253.
4. Chen, P. C. T., "Elastic-Plastic Analysis of a Radially Stressed Annular Plate," Journal of Applied Mechanics, Vol. 44, 1977, pp. 167-169.
5. Chen, P. C. T. and O'Hara, G. P., "Finite Element Solutions of Pressurized Thick Tubes," Proceedings of the Fifth Engineering Mechanics Division Specialty Conference, ASCE, 1984, pp. 1137-1140.
6. Prager, W., "The Theory of Plasticity: A Survey of Recent Achievements," Proceedings of the Institution of Mechanical Engineers, Vol. 169, 1955, pp. 41-57.
7. Ziegler, H., "A Modification of Prager's Hardening Rule," Q. Appl. Math., Vol. 17, 1959, pp. 55-65.
8. Bathe, K. J., "ADINA User's Manual," Report AE-81-1, ADINA Engineering Inc., Watertown, MA, 1981.

9. Armen, H., "Plasticity in General Software," Workshop on Inelastic Constitutive Equations for Metals, (E. Krempl, C. H. Wells, and Z. Zudans, Eds.) Rensselaer Polytechnic Institute, Troy, NY, 1975, pp. 56-78.
10. Noor, A. K., "Survey of Computer Programs for Solution of Nonlinear Structural and Solid Mechanics Problem," Computer and Structures, Vol. 13, 1981, pp. 425-465.




Figure 1. Effect of hardening on the relation between internal pressure and elastic-plastic interface.




Figure 2. Boundary displacement during loading and after unloading.




Figure 3. Distribution of hoop stresses during loading.




Figure 4. Distribution of residual hoop stresses.




Figure 5. Effect of hardening parameter on residual stress distribution.




Figure 6. Effect of hardening rules on residual stress distribution.

TECHNICAL REPORT INTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>
CHIEF, DEVELOPMENT ENGINEERING BRANCH	
ATTN: SMCAR-LCB-D	1
-DA	1
-DP	1
-DR	1
-DS (SYSTEMS)	1
-DS (ICAS GROUP)	1
-DC	1
CHIEF, ENGINEERING SUPPORT BRANCH	
ATTN: SMCAR-LCB-S	1
-SE	1
CHIEF, RESEARCH BRANCH	
ATTN: SMCAR-LCB-R	2
-R (ELLEN FOGARTY)	1
-RA	1
-RM	2
-RP	1
-RT	1
TECHNICAL LIBRARY	5
ATTN: SMCAR-LCB-TL	
TECHNICAL PUBLICATIONS & EDITING UNIT	2
ATTN: SMCAR-LCB-TL	
DIRECTOR, OPERATIONS DIRECTORATE	1
DIRECTOR, PROCUREMENT DIRECTORATE	1
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1

NOTE: PLEASE NOTIFY DIRECTOR, BENET WEAPONS LABORATORY, ATTN: SMCAR-LCB-TL,
OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
ASST SEC OF THE ARMY RESEARCH & DEVELOPMENT ATTN: DEP FOR SCI & TECH THE PENTAGON WASHINGTON, D.C. 20315	1	COMMANDER US ARMY AMCCOM ATTN: SMCAR-ESP-L ROCK ISLAND, IL 61299	1
COMMANDER DEFENSE TECHNICAL INFO CENTER ATTN: DTIC-DDA CAMERON STATION ALEXANDRIA, VA 22314	12	COMMANDER ROCK ISLAND ARSENAL ATTN: SMCRI-ENM (MAT SCI DIV) ROCK ISLAND, IL 61299	1
COMMANDER US ARMY MAT DEV & READ COMD ATTN: DRCDE-SG 5001 EISENHOWER AVE ALEXANDRIA, VA 22333	1	DIRECTOR US ARMY INDUSTRIAL BASE ENG ACTV ATTN: DRXIB-M ROCK ISLAND, IL 61299	1
COMMANDER ARMAMENT RES & DEV CTR US ARMY AMCCOM ATTN: SMCAR-LC SMCAR-LCE SMCAR-LCM (BLDG 321) SMCAR-LCS SMCAR-LCU SMCAR-LCW SMCAR-SCM-O (PLASTICS TECH EVAL CTR, BLDG. 351N) SMCAR-TSS (STINFO) DOVER, NJ 07801	1 1 1 1 1 1 1 2	COMMANDER US ARMY TANK-AUTMV R&D COMD ATTN: TECH LIB - DRSTA-TSL WARREN, MI 48090	1
		COMMANDER US ARMY TANK-AUTMV COMD ATTN: DRSTA-RC WARREN, MI 48090	1
DIRECTOR BALLISTICS RESEARCH LABORATORY ATTN: AMXBR-TSB-S (STINFO) ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER US MILITARY ACADEMY ATTN: CHMN, MECH ENGR DEPT WEST POINT, NY 10996	1
MATERIEL SYSTEMS ANALYSIS ACTV ATTN: DRXSY-MP ABERDEEN PROVING GROUND, MD 21005	1	US ARMY MISSILE COMD REDSTONE SCIENTIFIC INFO CTR ATTN: DOCUMENTS SECT, BLDG. 4484 REDSTONE ARSENAL, AL 35898	2
		COMMANDER US ARMY FGN SCIENCE & TECH CTR ATTN: DRXST-SD 220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	1

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH AND DEVELOPMENT CENTER,
US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, SMCAR-LCB-TL,
WATERVLIET, NY 12189, OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST (CONT'D)

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
COMMANDER US ARMY MATERIALS & MECHANICS RESEARCH CENTER ATTN: TECH LIB - DRXMR-PL WATERTOWN, MA 01272	2	DIRECTOR US NAVAL RESEARCH LAB ATTN: DIR, MECH DIV CODE 26-27, (DOC LIB) WASHINGTON, D.C. 20375	1 1
COMMANDER US ARMY RESEARCH OFFICE ATTN: CHIEF, IPO P.O. BOX 12211 RESEARCH TRIANGLE PARK, NC 27709	1	COMMANDER AIR FORCE ARMAMENT LABORATORY ATTN: AFATL/DLJ AFATL/DLJG EGLIN AFB, FL 32542	1 1
COMMANDER US ARMY HARRY DIAMOND LAB ATTN: TECH LIB 2800 POWDER MILL ROAD ADELPHIA, MD 20783	1	METALS & CERAMICS INFO CTR BATTELLE COLUMBUS LAB 505 KING AVENUE COLUMBUS, OH 43201	1
COMMANDER NAVAL SURFACE WEAPONS CTR ATTN: TECHNICAL LIBRARY CODE X212 DAHLGREN, VA 22448	1		

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH AND DEVELOPMENT CENTER,
US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, SMCAR-LCB-TL,
WATERVLIET, NY 12189, OF ANY ADDRESS CHANGES.

END

FILMED

1-86

DTIC